

**A selection of Stainless steel complying with BASTA and BVB
(Byggsvarubedömningen) properties criteria.**

| Grade EN | Grade UNS | Grade AISI | C | Cr | Ni | Mo | Other |
|-------------|---------------|---------------|------|------|------|-----|--------|
| 1.4301 | S30400 | 304 | 0,04 | 18,1 | 8,1 | | |
| 1.4307 | S30403 | 304L | 0,02 | 18,1 | 8,1 | | |
| 1.4401 | S31600 | 316 | 0,04 | 17,2 | 10,1 | 2,1 | |
| 1.4404 | S31603 | 316L | 0,02 | 17,1 | 10,1 | 2,1 | |
| 1.4436 | S31600 | 316 | 0,04 | 16,9 | 10,7 | 2,6 | |
| 1.4432 | S31603 | 316L | 0,02 | 16,9 | 10,7 | 2,6 | |
| 1.4162 | S32101 | - | 0,03 | 21,5 | 1,5 | 0,3 | Cu, Mn |
| 1.4462 | S31803/S32205 | - | 0,02 | 25,4 | 6,9 | 3,1 | |
| 1.4438 | S31703 | 317L | 0,02 | 18,2 | 13,7 | 3,1 | |
| 1.4547 | S31254 | - | 0,01 | 20,0 | 18,0 | 6,1 | Cu |
| 1.4362 | S32304 | - | 0,02 | 23,0 | 4,8 | 0,3 | Cu |
| 1.4662 | S82441 | - | 0,02 | 24,0 | 3,6 | 1,6 | Cu, Mn |
| 1.4439 | S31726 | 317LMN | 0,02 | 17,3 | 13,7 | 4,1 | |
| 1.4539 | N08904 | 904L | 0,01 | 20,0 | 25,0 | 4,3 | Cu |
| 1.4410 | S32750 | - | 0,02 | 25,0 | 7,0 | 4,0 | |

The table shows the typical composition. For further details on the composition refer to standard En- 10088-1 list of stainless steels. The above steel contains max. 0.03% sulfur.

2013-02-21

